

### AMENDMENTS TO CLAIMS

The status of all claims and the text of pending claims, with markings to show current changes relative to the immediately prior version, follows.

1. (Previously Presented) A method of quenching a material, comprising the steps of:  
providing a material having a first section and a second section; and  
impingement cooling said first section with a fluid to increase a cooling rate of said first section relative to a cooling rate of said second section;  
wherein impingement cooling is a subset of forced convection cooling that produces significantly higher heat transfer coefficients than the remainder of the forced convection regime.
2. (Original) The method as recited in claim 1, wherein said fluid comprises a gas.
3. (Original) The method as recited in claim 1, wherein said propelling step generally minimizes a gradient between a temperature of said first section and a temperature of said second section.
4. (Cancelled)
5. (Original) The method as recited in claim 1, wherein the propelling step remains constant during quenching.

6. (Original) The method as recited in claim 1, wherein the propelling step varies during quenching.
7. (Original) The method as recited in claim 6, wherein the propelling step varies by adjusting a pressure of said fluid.
8. (Previously Presented) A method of adjusting the cooling rate of a forging during quenching, comprising the steps of:
- providing a forging having a first section with a first cooling rate and a second section having a second cooling rate; and
  - impingement cooling said first section with a fluid in order to minimize a differential between said first cooling rate and said second cooling rate;
  - wherein impingement cooling is a subset of forced convection cooling that produces significantly higher heat transfer coefficients than the remainder of the forced convection regime.
9. (Original) The method as recited in claim 8, wherein said fluid is a gas.
10. (Original) The method as recited in claim 8, wherein said propelling step generally minimizes a gradient between a temperature of said first section and a temperature of said second section.
11. (Cancelled)

12. (Original) The method as recited in claim 8, wherein the propelling step remains constant during quenching.

13. (Original) The method as recited in claim 8, wherein the propelling step varies during quenching.

14. (Original) The method as recited in claim 13, wherein the propelling step varies by adjusting a pressure of said fluid.

15. (Previously Presented) An apparatus for quenching a material, the material having a first section and a second section, said apparatus comprising:

a support for receiving the material; and

an outlet having a size and a location adjacent said support such that a fluid exiting said outlet impingement cools the first section of the material, so that a cooling rate of the first section increases relative to a cooling rate of the second section;

wherein impingement cooling is a subset of forced convection cooling that produces significantly higher heat transfer coefficients than the remainder of the forced convection regime.

16. (Original) The apparatus as recited in claim 15, wherein said outlet has a diameter ( $d$ ) and is positioned a distance ( $Z$ ) from the material placed in said support, and  $Z/d$  is between approximately 1.0 and 6.0.

17. (Original) The apparatus as recited in claim 15, wherein said outlet comprises a plurality of outlets each having a diameter (d), adjacent outlets having a spacing (s) therebetween, and  $s/d$  is less than approximately 26.0.
18. (Original) The apparatus as recited in claim 17, wherein said spacing is a circumferential spacing (X) and  $X/d$  is less than approximately 26.0.
19. (Original) The apparatus as recited in claim 17, wherein said spacing is a radial spacing (Y) and  $Y/d$  is less than approximately 24.0.
20. (Original) The apparatus as recited in claim 15, wherein said outlet comprises a plurality of outlets in an annular pipe.
21. (Previously Presented) The method as recited in claim 1, further comprising the step of impingement cooling said second section.
22. (Previously Presented) The method as recited in claim 8, further comprising the step of impingement cooling said second section.
23. (Previously Presented) The method as recited in claim 1, wherein said impingement cooling step produces heat transfer coefficients up to approximately 300 BTU/hr ft<sup>2</sup> °F.

24. (Previously Presented) The method as recited in claim 1, wherein said first section has a low surface area to volume ratio.
25. (Previously Presented) The method as recited in claim 1, wherein said first section is a larger volumetric section than said second section.
26. (Previously Presented) The method as recited in claim 8, wherein said impingement cooling step produces heat transfer coefficients up to approximately 300 BTU/hr ft<sup>2</sup> °F.
27. (Previously Presented) The method as recited in claim 8, wherein said first section has a low surface area to volume ratio.
28. (Previously Presented) The method as recited in claim 8, wherein said first section is a larger volumetric section than said second section.
29. (Previously Presented) The apparatus as recited in claim 15, wherein said impingement cooling step produces heat transfer coefficients up to approximately 300 BTU/hr ft<sup>2</sup> °F.
30. (Previously Presented) The apparatus as recited in claim 20, wherein said outlet further comprises a plurality of outlets in a central section.

31. (Previously Presented) A method of quenching a material, comprising the steps of:  
providing a material having a first section and a second section; and  
cooling said first section with a gas to increase a cooling rate of said first section relative to a cooling rate of said second section;  
wherein said cooling step produces heat transfer coefficients greater than those created by oil bath quenching.
32. (Previously Presented) The method as recited in claim 31, wherein said cooling step comprises impingement cooling.
33. (Previously Presented) The method as recited in claim 31, wherein said cooling step produces heat transfer coefficients up to approximately 300 BTU/hr ft<sup>2</sup> °F.
34. (Previously Presented) A method of quenching a nickel alloy, comprising the steps of:  
impingement cooling said alloy at a cooling rate; and  
reducing said cooling rate once said alloy exits a temperature range of a ductility trough.
35. (Previously Presented) The method as recited in claim 34, wherein said nickel alloy is a course grain nickel alloy.
36. (Previously Presented) The method as recited in claim 35, wherein said temperature range is between approximately 1800-2100°F.

37. (New) The method as recited in claim 6, wherein the material is a nickel alloy.
38. (New) The method as recited in claim 37, wherein said impingement cooling step reduces said cooling rate once said alloy exits a temperature range of a ductility trough.